



ALMETALZ METAL

上海誉弘金属材料有限公司

TECHNICAL DATA SHEET

Description	Item No.	Treatment	Tensile Strength. Mpa	Yield Strength. Mpa	Elongation A50 %	Beng Radius	Total light Reflection	Diffuse Light Refelection
Silver Mirror	A180	Anodised	160-200	140-180	≥ 2	≥ 1.5 gauge of material	$\geq 86\%$	≤ 20
Silver Mirror	A181	Anodised	160-200	140-180	≥ 2	≥ 1.5 gauge of material	$\geq 86\%$	≤ 16
High Silver Mirror	A182	Anodised	160-200	140-180	≥ 2	≥ 1.5 gauge of material	$\geq 87\%$	≤ 9
Matt	A280	Anodised	160-185	150-175	≥ 2	≥ 1.5 gauge of material	$\geq 84\%$	80-85
Hammer Concave	A480	Anodised	160-185	125-165	≥ 2	≥ 1.5 gauge of material	$\geq 84\%$	≥ 82
Grille	A488	Anodised	150-190	140-170	≥ 2	≥ 1.5 gauge of material	--	--